



Contribution ID: 465

Type: **not specified**

P4.129 Investigation of beryllium damage under transient plasma heat loads in wide range of temperatures and heat loads

Thursday, 20 September 2018 11:00 (2 hours)

The first wall panels of the ITER main chamber will be completely armored with beryllium. The primary reasons for the selection of beryllium as an armor material for the ITER first wall are its low Z, high oxygen gettering characteristics and also high thermal conductivity. During plasma operation in the ITER, beryllium besides low cyclic heat loads (normal events) will be suffered by high transient heat loads, such as ELMs, disruptions, VDE, etc. (off normal events). These transient loads cause rapid heating of beryllium surface and can result in significant changes in surface and near-surface regions, such as material loss, melting, cracking, evaporation and formation of beryllium dust as well as hydrogen isotopes retention both in the armor and in the dust. It is expected that the erosion of beryllium under transient plasma loads such as ELMs and disruptions will have significant impact on lifetime of the ITER first wall.

This paper presents the main results of numerous experiments carried out during some last years at QSPA-Be plasma accelerator in Bochvar Institute. QSPA-Be plasma accelerator is capable to provide plasma (hydrogen or deuterium) and radiation heat loads on target surface relevant to ITER ELMs and mitigated disruptions. Special Be and Be/CuCrZr mock-ups were tested by hydrogen/deuterium plasma streams (5 cm in diameter) with pulse duration of 0.5 ms in a heat loads range of 0.2-2.2 MJ/m² and maximum quantities of plasma pulses up to 100-250 shots. The angle between plasma stream direction and mock-ups surface was 30°. During the experiments, the mock-ups temperature has been maintained in the range of RT-500°C. Two beryllium ITER grades: TGP-56FW (RF, Bochvar Institute) and S-65C (USA, Materion Brush) were studied in these experiments. Influences of plasma heat loads, surface temperature and quantities of plasma pulses on the Be erosion and surface damage are presented.

Presenter: KUPRIYANOV, Igor (Beryllium Technology Department A.A. Bochvar High Technology Research Institute of Inorganic Materials (JSC VNIINM))

Session Classification: P4